




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : H01L 33/00, C09K 11/78, 11/80, 11/82		A1	(11) International Publication Number: WO 00/33390
			(43) International Publication Date: 8 June 2000 (08.06.00)
(21) International Application Number: PCT/US99/28280 (22) International Filing Date: 30 November 1999 (30.11.99) (30) Priority Data: 09/203,212 30 November 1998 (30.11.98) US (71) Applicant: GENERAL ELECTRIC COMPANY [US/US]; 1 River Road, Schenectady, NY 12345 (US). (72) Inventors: SRIVASTAVA, Alok, Mani; 2A4 Sheridan Village, Schenectady, NY 12308 (US). LEVINSON, Lionel, Monty; 1 Linda Lane, Niskayuna, NY 12309 (US). BEERS, William, Winder; 11481 Chapin Street, Chesterland, OH 44026 (US). DUGGAL, Anil, Raj; 2322 Algonquin Road, Niskayuna, NY 12309 (US). (74) Agents: STECKLER, Henry, I. et al.; General Electric Com- pany, 3135 Easton Turnpike W3C, Fairfield, CT 06431 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.	

(54) Title: LIGHT EMITTING DEVICE WITH PHOSPHOR COMPOSITION

(57) Abstract

The invention relates to a light source comprising a phosphor composition and a light emitting device such as an LED or a laser diode. The phosphor composition absorbs radiation having a first spectrum and emits radiation having a second spectrum and comprises at least one of: $\text{YBO}_3\text{:Ce}^{3+}, \text{Tb}^{3+}$; $\text{BaMgAl}_{10}\text{O}_{17}\text{:Eu}^{2+}, \text{Mn}^{2+}$; $(\text{Sr}, \text{Ca}, \text{Ba})(\text{Al}, \text{Ga})_2\text{S}_4\text{:Eu}^{2+}$; and $\text{Y}_3\text{Al}_5\text{O}_{12}\text{:Ce}^{3+}$; and at least one of: $\text{Y}_2\text{O}_2\text{S:E}^{3+}, \text{Bi}^{3+}$; $\text{YVO}_4\text{:Eu}^{3+}, \text{Bi}^{3+}$; SrS:E^{2+} ; $\text{SrY}_2\text{S}_4\text{:Eu}^{2+}$; $\text{CaLa}_2\text{S}_4\text{:Ce}^{3+}$; and $(\text{Ca}, \text{Sr})\text{S:E}^{2+}$. The phosphor composition and the light source together can produce white light with pleasing characteristics, such as a color temperature of 3000–6500° K, a color rendering index of about 83–87, and a device luminous efficacy of about 10–20 lumens per watt.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

LIGHT EMITTING DEVICE WITH PHOSPHOR COMPOSITION

This application is a continuation-in-part of U.S. Serial No. 09/019,647, filed February 6, 1998.

BACKGROUND

Field of the Invention

- 5 This invention relates generally to light emitting devices, and more particularly to a light emitting diode (LED) or laser diode coated with phosphors.

Description of the Related Art

- 10 Solid state light sources have been available for many years. The colors have been predominantly red, orange, and green. Within the last several years blue LEDs have also been produced. The combination of red, green and blue LEDs has enabled the generation of white light with a complicated 4 lead package. However, the different LEDs have different lumen vs life curves causing the color to change with life. In the Fall of 1996, Nichia of Japan introduced a new white LED, Product No. NSPW310AS. This product uses yttrium aluminum garnet doped with cerium to convert blue emission from the LED into a very broad band yellow emission. The emission peak is at 580 nm with a full width at half maximum of 160 nm. The phosphor is coated directly on the LED. The entire device is encapsulated in a clear plastic lens. The emission contains enough orange emission to produce white light at a color temperature of about 8000° K, a color rendering index (CRI) of about 77, and a device luminous efficacy of approximately 5 lumens per watt (lm/w) of input electric power.
- 15
20

It is well know that tastes in lighting characteristics can vary by geographical region. For example, in some regions of the world, high color temperatures are preferred, while in other regions lower color temperatures are desired. Similarly, in some regions, CRIs in the mid-nineties are preferred, while in other regions CRIs in

the mid-eighties are preferred. Hence, it is desirable to adapt the output characteristics of a lamp to suit particular preferences.

The color temperature of the white LED produced by Nichia can be lowered by using more phosphor, however, the system efficiency is also decreased. There is a need for
 5 a phosphor-coated LED having a higher device luminous efficacy; there is also a need for such an LED having a lower color temperature.

SUMMARY

A light-emitting device, according to an exemplary embodiment of the invention,
 10 comprises a blue-emitting LED covered with a phosphor-containing covering, the phosphor-containing covering containing green-emitting phosphors and red-emitting phosphors, said green and red phosphors being excitable by said blue-emitting LED.

The invention also relates to a phosphor composition which absorbs radiation having a first spectrum and emits radiation having a second spectrum and which comprises at
 15 least one of: $\text{YBO}_3\text{:Ce}^{3+}, \text{Tb}^{3+}$; $\text{BaMgAl}_{10}\text{O}_{17}\text{:Eu}^{2+}, \text{Mn}^{2+}$; $(\text{Sr}, \text{Ca}, \text{Ba})(\text{Al}, \text{Ga})_2\text{S}_4\text{:Eu}^{2+}$; and $\text{Y}_3\text{Al}_5\text{O}_{12}\text{:Ce}^{3+}$; and at least one of: $\text{Y}_2\text{O}_2\text{S:Eu}^{3+}, \text{Bi}^{3+}$; $\text{YVO}_4\text{:Eu}^{3+}, \text{Bi}^{3+}$; SrS:Eu^{2+} ; $\text{SrY}_2\text{S}_4\text{:Eu}^{2+}$; $(\text{Ca}, \text{Sr})\text{S:Eu}^{2+}$; and $\text{CaLa}_2\text{S}_4\text{:Ce}^{3+}$ (where the element following the colon represents an activator).

The invention also relates to a novel phosphor composition comprising
 20 $\text{Y}_2\text{O}_2\text{S:Eu}^{3+}, \text{Bi}^{3+}$.

The invention also relates to a novel phosphor composition comprising $\text{YVO}_4\text{:Eu}^{3+}, \text{Bi}^{3+}$.

The invention also relates to a lamp comprising a phosphor composition and a light emitting device such as an LED or laser diode. The LED or laser diode emits
 25 radiation having a first spectrum, at least a portion of which is absorbed by the phosphor composition. The phosphor composition emits radiation having a second spectrum and comprises at least one of: $\text{YBO}_3\text{:Ce}^{3+}, \text{Tb}^{3+}$; $\text{BaMgAl}_{10}\text{O}_{17}\text{:Eu}^{2+}, \text{Mn}^{2+}$;

(Sr,Ca,Ba)(Al,Ga)₂S₄:Eu²⁺; and Y₃Al₅O₁₂-Ce³⁺; and at least one of: Y₂O₂S:Eu³⁺,Bi³⁺; YVO₄:Eu³⁺,Bi³⁺; SrS:Eu²⁺; SrY₂S₄:Eu²⁺; (Ca,Sr)S:Eu²⁺; and CaLa₂S₄:Ce³⁺.

5 The invention also relates to a light emitting device comprising a blue emitting LED and a phosphor composition comprising SrS:Eu²⁺,Ce³⁺,K⁺. The SrS:Eu²⁺,Ce³⁺,K⁺ phosphor, when excited by blue light, emits a broadband spectrum including red light and green light.

10 The invention also relates to a method of producing white light comprising the steps of generating light, directing the light to a phosphor composition comprising at least one of: YBO₃:Ce³⁺,Tb³⁺; BaMgAl₁₀O₁₇:Eu²⁺,Mn²⁺; (Sr,Ca,Ba)(Al,Ga)₂S₄:Eu²⁺; and Y₃Al₅O₁₂-Ce³⁺; and at least one of: Y₂O₂S:Eu³⁺,Bi³⁺; YVO₄:Eu³⁺,Bi³⁺; SrS:Eu²⁺; SrY₂S₄:Eu²⁺; (Ca,Sr)S:Eu²⁺; and CaLa₂S₄:Ce³⁺; and converting at least a portion of the light with the phosphor composition to light having a different spectrum.

15 The phosphor composition and the light source together can produce white light with pleasing characteristics, such as a color temperature of 3000-4100° K, a color rendering index of greater than 70, typically greater than 80, for example about 83-87, and a device luminous efficacy of about 10-20 lumens per watt of input electric power.

20 BRIEF DESCRIPTION OF THE DRAWINGS

Other features and advantages of the invention will be apparent from the following detailed description and the accompanying drawings, in which:

FIG. 1 is a schematic elevational view in cross-section of a phosphor-coated LED of the present invention;

25 FIG. 2 is a schematic elevational view in cross-section of a phosphor-coated LED of the present invention;

FIG. 3 is a schematic elevational view of a cross section of a lamp which includes a laser diode and a phosphor composition according to another embodiment of the invention; and

FIG. 4 is an emission spectrum of the phosphor $\text{SrS:Eu}^{2+}, \text{Ce}^{3+}, \text{K}^+$.

5

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Parts are parts by weight and percents are weight percents unless otherwise indicated or apparent. When a preferred range such as 5-25 is given, this means preferably at least 5 and preferably not more than 25.

- 10 Some of the more important parameters used to describe the output spectrum of a light source are the color temperature, the color rendering index, and the device luminous efficacy. The color temperature of an output spectrum is not an exact representation of the color of a light source. The color temperature of a light source refers to the temperature of a blackbody source having the closest color match to the
- 15 light source in question. The color match is typically represented and compared on a conventional CIE (Commission International de l'Eclairage) chromaticity diagram. See, for example, "Encyclopedia of Physical Science and Technology", vol. 7, 230-231 (Robert A. Meyers ed., 1987). Generally, as the color temperature increases, the light becomes more blue. As the color temperature decreases, the light appears more
- 20 red.

- The color rendering index (CRI) is a measure of the degree of distortion in the apparent colors of a set of standard pigments when measured with the light source in question as opposed to a standard light source. The CRI can be determined by calculating the color shift, e.g. quantified as tristimulus values, produced by the light
- 25 source in question as opposed to the standard light source. Typically, for color temperatures below 5000° K, the standard light source used is a blackbody of the appropriate temperature. For color temperatures greater than 5000° K, sunlight is typically used as the standard light source. Light sources having a relatively

continuous output spectrum, such as incandescent lamps, typically have a high CRI, e.g. equal to or near 100. Light sources having a multi-line output spectrum, such as high pressure discharge lamps, typically have a CRI ranging from about 50 to 80. Fluorescent lamps typically have a CRI greater than about 60.

- 5 The device luminous efficacy is defined as the luminous flux output by the lamp divided by the electric power input to the lamp. The device luminous efficacy of the lamp takes into account the spectral luminous efficacy (luminous flux out divided by radiant power in), the device efficiency (radiant power output by the LED divided by electric power input to the LED), the quantum efficiency of the phosphor composition
10 (number of photons emitted by the phosphor divided by the number of photons absorbed by the phosphor), and the energy loss associated with the decrease in frequency of the emitted light (equal to $h\Delta\nu$, where h is Plank's constant and $\Delta\nu$ is the change in frequency of the light).

- Exemplary embodiments of the present invention include an LED and a phosphor
15 composition which together produce white light having pleasing characteristics. For example, the LED and phosphor composition can produce light having color temperatures between 3000° K and 6500° K, among other temperatures, for example 3000, 3500, 4100, 5000, and 6500 °K. The exemplary phosphor compositions can also produce a relatively high CRI, e.g. typically greater than 70, preferably greater
20 than 80, e.g. 83-87, and a high device luminous efficacy, e.g., 10-20 lumens per watt or more of input electric power.

- With reference to FIG. 1, there is shown a phosphor-coated LED or light-emitting device 10 having a blue-emitting LED 12 covered with a phosphor-containing layer or covering 14 (a phosphor coating directly on the LED), and a clear polymer lens 16.
25 With reference to FIG. 2, there is shown a phosphor-coated LED or light-emitting device 10 having a blue-emitting LED 12 covered with a phosphor-containing layer or covering 15 (phosphors embedded in polymer), and a clear polymer lens 16 molded over layer 15. The lens 16 may also be a diffuse lens which scatters light propagating through it. The lens 16 and the layer 15 may also comprise a silicone
30 material, for example.

Blue-emitting LED 12 has an emission peak at 420-470, more typically 430-460, more typically 440-450, optionally about 450-470, nm, typically with a full width at half maximum of not more than 70, more typically 50, more typically 30, nm. Blue-emitting LEDs of this type are known in the art, a preferred example thereof is available from Nichia of Japan as Product No. NSCB100. LED 12 preferably has a device efficiency (radiant power out of LED divided by electric power in) of at least 4%, more preferably 6%, more preferably 8%. Blue-emitting LEDs are generally known in the art.

According to one example of the invention, a combination of two blue-excited phosphors (excited by the blue emission from LED 12), one emitting in the green and one emitting in the red, is used in place of the yellow emitting yttrium aluminum garnet of the Nichia product mentioned above. Because these new emissions are close to peaks in the tristimulus functions in combination with the blue from the LED they produce light with higher luminous efficacy and better color rendering than the phosphors used in prior devices. These green and red phosphors are selected so that they are excited by the blue-emitting LED. The green color-emitting phosphor typically has an emission peak at 510-560, more typically 530-555, more typically 540-550, for example about 545, nm, with a full width at half maximum of not more than 60, typically not more than 50, 35, 20, 10, or 5, nm. The red color-emitting phosphor typically has an emission peak at 600-630, more typically 610-625, more typically 610-615, optionally about 611, nm, with a full width at half maximum of not more than 100, typically not more than 60, 50, 20, 10, or 5, nm. The phosphor-containing layers 14 and 15 contain these green color-emitting phosphors and red color-emitting phosphors. These phosphors typically have preferred particle size of 2-5 micrometers.

One example of a phosphor composition comprises at least one of the following green-emitting phosphors: $\text{YBO}_3\text{:Ce}^{3+}, \text{Tb}^{3+}$; $\text{BaMgAl}_{10}\text{O}_{17}\text{:Eu}^{2+}, \text{Mn}^{2+}$; and $(\text{Sr}, \text{Ca}, \text{Ba})(\text{Al}, \text{Ga})_2\text{S}_4\text{:Eu}^{2+}$; in combination with at least one of the following red-emitting phosphors: $\text{Y}_2\text{O}_2\text{S}\text{:Eu}^{3+}, \text{Bi}^{3+}$; $\text{YVO}_4\text{:Eu}^{3+}, \text{Bi}^{3+}$; $\text{SrS}\text{:Eu}^{2+}$; $\text{SrY}_2\text{S}_4\text{:Eu}^{2+}$; $\text{CaLa}_2\text{S}_4\text{:Ce}^{3+}$; and $(\text{Ca}, \text{Sr})\text{S}\text{:Eu}^{2+}$.

In the above phosphors, the element following the colon represents an activator. The notation (A,B,C) signifies (A_x, B_y, C_z) where $0 \leq x \leq 1$ and $0 \leq y \leq 1$ and $0 \leq z \leq 1$ and $x+y+z=1$. For example, (Sr,Ca,Ba) signifies (Sr_x, Ca_y, Ba_z) where $0 \leq x \leq 1$ and $0 \leq y \leq 1$ and $0 \leq z \leq 1$ and $x+y+z=1$. Typically, x, y, and z are all nonzero. The notation (A,B)
 5 signifies (A_x, B_y) where $0 \leq x \leq 1$ and $0 \leq y \leq 1$ and $x+y=1$. Typically, x and y are both nonzero.

The green-emitting phosphors, when excited by blue light, have the following characteristics: $YBO_3:Ce^{3+}, Tb^{3+}$ has an emission peak at about 545 nm and a full width half maximum value of about 2 nm; $BaMgAl_{10}O_{17}:Eu^{2+}, Mn^{2+}$ has an emission
 10 peak at about 515 nm and a full width half maximum value of about 50 nm; and $(Sr,Ca,Ba)(Al,Ga)_2S_4:Eu^{2+}$ has an emission peak at about 540 nm and a full width half maximum value of about 50 nm.

The red-emitting phosphors, when excited by blue light, have the following characteristics: $Y_2O_2S:Eu^{3+}, Bi^{3+}$ has an emission peak at about 620 nm and a full
 15 width half maximum value of about 2 nm; $YVO_4:Eu^{3+}, Bi^{3+}$ has an emission peak at about 620 nm and a full width half maximum value of about 2 nm; $SrS:Eu^{2+}$ has an emission peak at about 610 nm and a full width half maximum value of about 70 nm; $(Ca,Sr)S:Eu^{2+}$ has an emission peak at about 610 nm and a full width half maximum value of about 50 nm; $SrY_2S_4:Eu^{2+}$ has an emission peak at about 645 nm and a full
 20 width half maximum value of about 100 nm; and $CaLa_2S_4:Ce^{3+}$ has an emission peak at about 600 nm and a full width half maximum value of about 100 nm.

The red and green phosphors are preferably blended in weight ratios such that combined with the blue emission of the LED, they produce suitable white light, e.g.,
 25 about 45/20 (weight ratio of red to green) for white light at about 3000° K; about 42/22 at about 3500° K; about 34/25 at about 4100° K; about 27/25 at about 5000° K; and about 20/25 at about 6500° K. The desired emission can also be obtained from Eu^{3+} (red) and Tb^{3+} (green). Alternative activators include Mn^{2+} and Eu^{2+} for green emission.

- The red phosphors $\text{Y}_2\text{O}_2\text{S}:\text{Eu}^{3+},\text{Bi}^{3+}$ and $\text{YVO}_4:\text{Eu}^{3+},\text{Bi}^{3+}$ have relatively narrow output spectra, e.g. full width half maximum values of less than about 5 nm, typically about 2 nm. The green phosphor $\text{YBO}_3:\text{Ce}^{3+},\text{Tb}^{3+}$ also has a relatively narrow output spectrum, e.g. a full width half maximum value of less than about 5 nm, typically about 2 nm. A combination of $\text{Y}_2\text{O}_2\text{S}:\text{Eu}^{3+},\text{Bi}^{3+}$ and/or $\text{YVO}_4:\text{Eu}^{3+},\text{Bi}^{3+}$ with $\text{YBO}_3:\text{Ce}^{3+},\text{Tb}^{3+}$ provides a phosphor composition which efficiently converts blue light into luminous flux. The efficiency of these phosphors is related to the variable sensitivity of the eye to different wavelengths of light. In the red region of the spectrum, the sensitivity of the eye drops off sharply at wavelengths greater than about 650 nm. Broad band red phosphors may have an emission spectrum with an appreciable portion of the emission greater than 650 nm where the eye is not sensitive. With sharp line red phosphors such as $\text{Y}_2\text{O}_2\text{S}:\text{Eu}^{3+},\text{Bi}^{3+}$ and $\text{YVO}_4:\text{Eu}^{3+},\text{Bi}^{3+}$, substantially all of the emission spectrum lies within the most sensitive region of the eye for red light, producing a higher luminous flux than a broad band red phosphor. In general, the sensitivity of the eye in the green wavelengths does not drop off as rapidly as in the red wavelengths, so that it is less important to have a green phosphor with a sharp line emission. However, a phosphor such as $\text{YBO}_3:\text{Ce}^{3+},\text{Tb}^{3+}$ which has a sharp line emission near the most sensitive green region of the spectrum (555 nm) also efficiently produces luminous flux.
- 20 The red emitting phosphor $\text{Y}_2\text{O}_2\text{S}:\text{Eu}^{3+},\text{Bi}^{3+}$ can be prepared by combining stoichiometric amounts of Y_2O_3 , Eu_2O_3 , Bi_2O_3 , and V_2O_5 and milling in a ball mill for about 2 hours. The mixture is then air fired in a furnace at about 1000° C for about 10 hours. The inclusion of bismuth increases the wavelength of light which is absorbed by the phosphor, such that blue light is absorbed.
- 25 The red emitting phosphor $\text{YVO}_4:\text{Eu}^{3+},\text{Bi}^{3+}$ can be prepared by combining stoichiometric amounts of Y_2O_3 , Eu_2O_3 , and Bi_2O_3 , and milling in a ball mill for about 2 hours. The mixture is then heated in an atmosphere of H_2S at about 1000° C for about 3 hours. The inclusion of bismuth increases the wavelength of light which is absorbed by the phosphor, such that blue light is absorbed.

According to another embodiment of the invention, a blue emitting LED is combined with a white emitting phosphor to produce white light. An example of a white-emitting phosphor is $\text{SrS:Eu}^{2+}, \text{Ce}^{3+}, \text{K}^{+}$, which, as shown in Figure 4, has a broad emission. $\text{SrS:Eu}^{2+}, \text{Ce}^{3+}, \text{K}^{+}$ can be used to generate white light with a suitable excitation, e.g. a blue LED emitting at about 425-430 nm, wherein the red part of the spectrum is provided by SrS:Eu^{2+} and the blue-green part of the spectrum by SrS:Ce^{3+} .

According to another embodiment of the invention, a blue emitting LED is combined with a yellow phosphor and a red phosphor to produce white light. Typically, the yellow phosphor has an emission peak of about 570-590 nm, and the red phosphor has an emission peak of about 600-650 nm. The first phosphor may comprise yttrium-aluminum-garnet doped with trivalent cerium ($\text{Y}_3\text{Al}_5\text{O}_{12}\text{-Ce}^{3+}$), for example, which emits a relatively broad yellow spectrum having an emission peak at about 580 nm and a full width half maximum value of about 160 nm. The second phosphor emits red light and may comprise at least one of the above-described red phosphors, $\text{Y}_2\text{O}_2\text{S:Eu}^{3+}, \text{Bi}^{3+}$; $\text{YVO}_4\text{:Eu}^{3+}, \text{Bi}^{3+}$; SrS:Eu^{2+} ; $\text{SrY}_2\text{S}_4\text{:Eu}^{2+}$; $\text{CaLa}_2\text{S}_4\text{:Ce}^{3+}$; and $(\text{Ca}, \text{Sr})\text{S:Eu}^{2+}$.

The red and yellow phosphors are preferably blended in weight ratios such that combined with the blue emission of the LED, they produce suitable white light, e.g., about 45/20 (weight ratio of red to yellow) for white light at about 3000° K; about 42/22 at about 3500° K; about 34/25 at about 4100° K; about 27/25 at about 5000° K; and about 20/25 at about 6500° K.

To apply the phosphor-containing layer to the LED, the red and green or yellow (hereinafter "green/yellow") phosphors or the white phosphor ($\text{SrS:Eu}^{2+}, \text{Ce}^{3+}, \text{K}^{+}$) may be dry blended in a suitable blender and then added to a liquid suspension medium or the individual phosphor or phosphors may be added to a liquid suspension, such as the nitrocellulose/butyl acetate binder and solvent solution used in commercial lacquers. Many other liquids including water with a suitable dispersant and thickener or binder, such as polyethylene oxide, can be used. The phosphor-containing suspension is painted or coated or otherwise applied on the LED and dried. To

provide layer 15 (see FIG. 2), the phosphor or phosphors are combined in suitable liquid polymer system, such as polypropylene, polycarbonate, or polytetrafluoroethylene, which is then coated or applied to the LED and dried, solidified, hardened, or cured. The liquid polymer system may optionally be UV
5 (ultraviolet) cured or room temperature cured, to minimize any heat damage to the LED. The clear polymer lens 16 made of suitable plastic such as polycarbonate or other rigid transparent plastic is then molded over the coated LED. Lens 16 may be further coated with anti-reflective layers to facilitate light escaping the device.

10 The total thickness of the phosphor coating should be such as to absorb most of the blue radiation while allowing some blue radiation to penetrate, or get through, to give the desired color or white light.

Less preferably the green/yellow phosphor may be coated on the LED in a separate layer from the red phosphor layer (the layers together forming a green/yellow and red phosphor-containing covering), although the total amounts of green/yellow and red
15 phosphors will preferably not change from the amounts noted above.

Upon application of a current, the LED produces a blue light, at least a portion of which is converted to red light and green/yellow light. The combination of blue, red, and green/yellow light produces a pleasing white light having a preferred combination of parameters such as a color temperature of between 3000° K and 6500° K, a CRI of
20 greater than 70, typically greater than 80, e.g. between about 83 and 87, and a device luminous efficacy of 10-20 lumens per watt of input electric power.

A preferred phosphor-coated LED of this invention provides 11 lumens per watt at a color temperature of 5000° K with a blue LED that is 4% efficient. As the LED efficiency increases, the lumens per watt of the invented device increases
25 proportionately. The present invention optimizes luminous efficiency, analogous to a triphosphor fluorescent lamp. The present invention, when energized, produces white light similar to a triphosphor fluorescent lamp. The red and green/yellow components are provided by the red and green/yellow phosphors or by the white phosphor ($\text{SrS:Eu}^{2+}, \text{Ce}^{3+}, \text{K}^+$); the blue component is provided by the blue LED.

FIG. 3 illustrates yet another embodiment of a light emitting device 30 which includes a blue-emitting laser diode 32, a transmissive body 36, and a phosphor layer 34. The blue-emitting laser diode 32 typically has an emission peak at 420-470, more typically 430-460, more typically 440-450 nm, with a full width at half maximum typically less than 10 nm, more typically less than 5 nm. Blue laser diodes are known in the art. See, for example, U.S. Patent Nos. Nos. 5,583,879, 5,604,763, and 5,644,584 and Shuji Nakamura and Gerhard Fasol, "The Blue Laser Diode" (1997). The transmissive body 36 may be formed of a suitable plastic such as polycarbonate or other rigid transparent plastic or a silicone material, for example. The transmissive body 36 may be clear or may be a diffuse body which scatters light passing through it. The phosphor layer 34 comprises a white phosphor or a red phosphor and a green/yellow phosphor, as described above, which efficiently absorb blue light from the laser diode.

The light emitting device 30 may also include a plurality of scattering particles 38 which are embedded in a transmissive material comprising, for example, a glass or a polymer or a silicone material. The scattering particles may comprise Al_2O_3 particles such as CR30 alumina powder available from Baikowski or TiO_2 particles, for example. The particles 38 effectively scatter the coherent light emitted from the laser diode 32, preferably with a negligible amount of absorption. The coupling of the diffuse scattered laser light with the phosphor material is advantageous in reducing optical saturation effects and physical damage of the phosphor material.

Although the preferred embodiments of the invention have been shown and described, it should be understood that various modifications may be resorted to without departing from the scope of the invention as disclosed and claimed herein.

WHAT IS CLAIMED IS:

1. A light-emitting device comprising a blue-emitting LED covered with a phosphor-containing covering, the phosphor-containing covering containing green-emitting phosphors and red-emitting phosphors, said green and red phosphors being excitable by said blue-emitting LED.
5
2. A device according to claim 1, said blue emitting LED having an emission peak at 420-470 nm with a full width at half maximum of not more than 70 nm.
10
3. A device according to claim 1, said green phosphors having an emission peak at 530-555 nm with a full width at half maximum of not more than 35 nm.
4. A device according to claim 1, said red phosphors having an emission peak at 610-625 nm with a full width at half maximum of not more than 20 nm.
15
5. A device according to claim 2, said green phosphors having an emission peak at 530-555 nm with a full width at half maximum of not more than 35 nm, said red phosphors having an emission peak at 610-625 nm with a full width at half maximum of not more than 20 nm.
20
6. A device according to claim 5, said device when energized producing white light and having a CRI greater than 70.

7. A device according to claim 6, further comprising a clear polymer lens over said phosphor-containing covering.

5 8. A device according to claim 5, said device when energized having a CRI greater than 80.

9. A device according to claim 5, said red phosphors having an emission peak at about 611 nm.

10 10. A device according to claim 9, said green phosphors having an emission peak at about 545 nm.

11. A phosphor composition which absorbs radiation having a first spectrum and emits radiation having a second spectrum, the phosphor composition comprising:

15 at least one of:

$\text{YBO}_3:\text{Ce}^{3+}, \text{Tb}^{3+};$

$\text{BaMgAl}_{10}\text{O}_{17}:\text{Eu}^{2+}, \text{Mn}^{2+};$

$(\text{Sr}, \text{Ca}, \text{Ba})(\text{Al}, \text{Ga})_2\text{S}_4:\text{Eu}^{2+};$ and

$\text{Y}_3\text{Al}_5\text{O}_{12}:\text{Ce}^{3+};$ and

20 at least one of:

$\text{Y}_2\text{O}_2\text{S}:\text{Eu}^{3+}, \text{Bi}^{3+};$

$\text{YVO}_4:\text{Eu}^{3+}, \text{Bi}^{3+};$

SrS:Eu^{2+} ;

$\text{SrY}_2\text{S}_4\text{:Eu}^{2+}$;

$\text{CaLa}_2\text{S}_4\text{:Ce}^{3+}$; and

$(\text{Ca,Sr})\text{S:Eu}^{2+}$.

5

12. The phosphor composition of claim 11, wherein the phosphor composition comprises $(\text{Sr,Ca,Ba})(\text{Al,Ga})_2\text{S}_4\text{:Eu}^{2+}$; and $(\text{Ca,Sr})\text{S:Eu}^{2+}$.

10

13. The phosphor composition of claim 11, wherein the phosphor composition comprises $\text{Y}_3\text{Al}_5\text{O}_{12}\text{-Ce}^{3+}$ and SrS:Eu^{2+} .

14. The phosphor composition of claim 11, wherein the

phosphor composition comprises at least one of $\text{Y}_2\text{O}_2\text{S:Eu}^{3+}, \text{Bi}^{3+}$ and $\text{YVO}_4\text{:Eu}^{3+}, \text{Bi}^{3+}$.

15

15. The phosphor composition of claim 14, wherein the phosphor composition comprises $\text{YBO}_3\text{:Ce}^{3+}, \text{Tb}^{3+}$.

20

16. The phosphor composition of claim 11, wherein the first spectrum includes blue light.

17. The phosphor composition of claim 16 wherein the blue light has an emission peak between about 450 nm and about 470 nm.

5 18. The phosphor composition of claim 11, wherein the second spectrum includes a first component having an emission peak at about 570-590 nm and a second component having an emission peak at about 600-650 nm.

10 19. The phosphor composition of claim 11, wherein the second spectrum includes a first component having an emission peak at about 540-550 nm and a second component having an emission peak at about 610-615 nm.

20. A lamp comprising:

a light emitting device; and

15 a phosphor composition which absorbs radiation having a first spectrum from the light emitting device and emits radiation having a second spectrum, the phosphor composition comprising:

at least one of:

$\text{YBO}_3:\text{Ce}^{3+}, \text{Tb}^{3+};$

$\text{BaMgAl}_{10}\text{O}_{17}:\text{Eu}^{2+}, \text{Mn}^{2+};$

20 $(\text{Sr}, \text{Ca}, \text{Ba})(\text{Al}, \text{Ga})_2\text{S}_4:\text{Eu}^{2+};$ and

$\text{Y}_3\text{Al}_5\text{O}_{12}:\text{Ce}^{3+};$ and

at least one of:

$\text{Y}_2\text{O}_2\text{S}:\text{Eu}^{3+}, \text{Bi}^{3+};$

$\text{YVO}_4:\text{Eu}^{3+},\text{Bi}^{3+};$

$\text{SrS}:\text{Eu}^{2+};$

$\text{SrY}_2\text{S}_4:\text{Eu}^{2+};$

$\text{CaLa}_2\text{S}_4:\text{Ce}^{3+};$ and

5 $(\text{Ca},\text{Sr})\text{S}:\text{Eu}^{2+}.$

21. The lamp of claim 20, wherein the light emitting device comprises a light emitting diode.

10 22. The lamp of claim 20, wherein the light emitting device comprises a laser diode.

23. The lamp of claim 20, wherein the phosphor composition comprises $(\text{Sr},\text{Ca},\text{Ba})(\text{Al},\text{Ga})_2\text{S}_4:\text{Eu}^{2+};$ and $(\text{Ca},\text{Sr})\text{S}:\text{Eu}^{2+}.$

15

24. The lamp of claim 20, wherein the phosphor composition comprises $\text{Y}_3\text{Al}_5\text{O}_{12}-\text{Ce}^{3+}$ and $\text{SrS}:\text{Eu}^{2+}.$

20 25. The lamp of claim 20, wherein the phosphor composition comprises at least one of $\text{Y}_2\text{O}_2\text{S}:\text{Eu}^{3+},\text{Bi}^{3+}$ and $\text{YVO}_4:\text{Eu}^{3+},\text{Bi}^{3+}.$

26. The phosphor composition of claim 25, wherein the phosphor composition comprises $\text{YBO}_3:\text{Ce}^{3+}, \text{Tb}^{3+}$.

27. A method of producing white light comprising the steps of:

5 generating light;

directing the light to a phosphor composition comprising:

at least one of:

$\text{YBO}_3:\text{Ce}^{3+}, \text{Tb}^{3+}$;

$\text{BaMgAl}_{10}\text{O}_{17}:\text{Eu}^{2+}, \text{Mn}^{2+}$; $(\text{Sr}, \text{Ca}, \text{Ba})(\text{Al}, \text{Ga})_2\text{S}_4:\text{Eu}^{2+}$; and

10 $\text{Y}_3\text{Al}_5\text{O}_{12}:\text{Ce}^{3+}$; and

at least one of:

$\text{Y}_2\text{O}_2\text{S}:\text{Eu}^{3+}, \text{Bi}^{3+}$;

$\text{YVO}_4:\text{Eu}^{3+}, \text{Bi}^{3+}$;

$\text{SrS}:\text{Eu}^{2+}$;

15 $\text{SrY}_2\text{S}_4:\text{Eu}^{2+}$;

$\text{CaLa}_2\text{S}_4:\text{Ce}^{3+}$; and

$(\text{Ca}, \text{Sr})\text{S}:\text{Eu}^{2+}$; and

converting at least a portion of the light with the phosphor composition to light having a different spectrum.

20

28. A light-emitting device comprising a blue-emitting LED covered with a phosphor-containing covering, the phosphor-containing covering containing a green-emitting phosphor and a red-emitting phosphor, the green and red emitting phosphors being excitable by said blue-emitting LED, the green and red emitting phosphors each having a full width half maximum value of less than 60.

5

29. The light emitting device of claim 28, wherein the green emitting phosphor has a peak emission at about 510-560 nm, and the red emitting phosphor has a peak emission at about 600-630 nm.

10

30. The light emitting device of claim 28, wherein the red emitting phosphor has a full width half maximum value of less than about 5 nm.

15

31. The light emitting device of claim 30, wherein the red emitting phosphor comprises at least one of $\text{Y}_2\text{O}_2\text{S}:\text{Eu}^{3+}, \text{Bi}^{3+}$ and $\text{YVO}_4:\text{Eu}^{3+}, \text{Bi}^{3+}$.

32. A light emitting device comprising:

a blue emitting LED; and

a phosphor composition comprising $\text{SrS}:\text{Eu}^{2+}, \text{Ce}^{3+}, \text{K}^+$.

20

33. The light emitting device of claim 32, wherein the blue LED has a peak emission between about 425 nm and about 430 nm.

34. A phosphor composition comprising $\text{Y}_2\text{O}_2\text{S}:\text{Eu}^{3+},\text{Bi}^{3+}$.

35. A phosphor composition comprising $\text{YVO}_4:\text{Eu}^{3+},\text{Bi}^{3+}$.

1/2

FIG. 1







FIG. 2



2/2

FIG. 3**FIG. 4**

INTERNATIONAL SEARCH REPORT

Internal Application No
PCT/US 99/28280

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 H01L33/00 C09K11/78 C09K11/80 C09K11/82

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 H01L C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	DE 197 56 360 A (PHILIPS PATENTVERWALTUNG) 10 September 1998 (1998-09-10) the whole document	1-11, 14, 19-21, 25, 27-29
Y	WO 98 19290 A (TEWS HELMUT ; AVERBECK ROBERT (DE); SIEMENS AG (DE)) 7 May 1998 (1998-05-07) page 3, line 8 - page 4, line 4	1-10, 28, 29
A	-/-	16, 17, 22

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

* & * document member of the same patent family

Date of the actual completion of the international search

17 March 2000

Date of mailing of the international search report

25/04/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel: (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

De Laere, A

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/28280

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DATTA: "Bismuth in Yttrium Vanadate and Yttrium Europium Vanadate Phosphors" JOURNAL OF THE ELECTROCHEMICAL SOCIETY., vol. 114, no. 10, October 1967 (1967-10), pages 1057-1063, XP002133419 ELECTROCHEMICAL SOCIETY. MANCHESTER, NEW HAMPSHIRE., US ISSN: 0013-4651 the whole document	35
Y		11,14, 19-21, 25,27 30,31
A		
X	US 5 813 753 A (RONDA CORNELIS ET AL) 29 September 1998 (1998-09-29) column 1, line 20-22 column 3, line 52-56	1
X	S.Z.TOMA: "Energy transfer and fluorescence process in Bi ³⁺ and Eu ³⁺ activated YVO ₄ " JOURNAL OF THE ELECTROCHEMICAL SOCIETY., vol. 114, no. 9, September 1967 (1967-09), pages 953-955, XP002133420 ELECTROCHEMICAL SOCIETY. MANCHESTER, NEW HAMPSHIRE., US ISSN: 0013-4651 the whole document	35
X	DE 34 06 798 A (SIEMENS AG) 29 August 1985 (1985-08-29) abstract	34
P,X	US 5 959 316 A (LOWERY CHRISTOPHER HAYDN) 28 September 1999 (1999-09-28) claim 13	1
A	DE 196 38 667 A (SIEMENS AG) 2 April 1998 (1998-04-02) column 6, line 36-41; claims 1,4	1-3,7, 10-13, 16,17, 20-24, 27,28,33

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/28280

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 19756360 A	10-09-1998	EP 0907970 A WO 9839805 A DE 19802046 A EP 0907971 A WO 9839806 A	14-04-1999 11-09-1998 17-09-1998 14-04-1999 11-09-1998
WO 9819290 A	07-05-1998	DE 19645035 C CN 1212069 A EP 0873557 A US 5994722 A	30-04-1998 24-03-1999 28-10-1998 30-11-1999
US 5813753 A	29-09-1998	EP 0922305 A WO 9854929 A	16-06-1999 03-12-1998
DE 3406798 A	29-08-1985	NONE	
US 5959316 A	28-09-1999	DE 19919381 A GB 2341274 A	09-03-2000 08-03-2000
DE 19638667 A	02-04-1998	BR 9706787 A BR 9709998 A CN 1228873 A WO 9750132 A WO 9812757 A EP 0862794 A EP 0907969 A JP 11500584 T	13-04-1999 10-08-1999 15-09-1999 31-12-1997 26-03-1998 09-09-1998 14-04-1999 12-01-1999